

TECHNICAL DATA SHEET

20 mm – Glossy

3200x1600x20 mm GLOSSY GL

PHYSICAL-CHEMICAL PROPERTIES	STANDARD TEST	REQUIRED VALUE	AVERAGE VALUE
Water absorbtion	ISO 10545-3	≤ 0,5%	≤ 0,1%
Breaking strenght	ISO 10545-4	≥ 1300 N	> 11000 N
Modulus of rupture	ISO 10545-4	R ≥ 35 N/mm2	≥ 45 N/mm2
Impact resistance	ISO-10545-5	Declared value ≥ 0,55 without damage	≥ 0,8
Linear thermal expansion	ISO 10545-8	Declared value	5,7.10-6 °C
Thermal shock resistance	ISO 10545-9	Samples must show no visible defects	Resist
Moisture expansion	ISO 10545-10	Declared value	< 0,1 mm/m
Carzing resistance	ISO 10545-11	Samples must show no surface crazing	Resist
Frost resistance	ISO 10545-12	Samples must show no visible damage	Resist
Chemical resistance: cleaning products	ISO-10545-13	GB	GA
Chemical resistance: swimming pool salts	ISO-10545-13	GB	GA
Chemical resistance: low concentration acids	ISO-10545-13	Declared value	GLB
Chemical resistance: low concentration bases	ISO-10545-13	Declared value	GLB
Resistance to stains	ISO 10545-14	Declared value	5
Determiration of lead and cadmium	ISO 10545-15	Declared value	Cadmium < 0,01 mg/l Lead < 0,1 mg/l
Scratch hardness	UNE 67-101	Declared value	Declared value: min 4
Dry heat resistance	EN 13310	Declared value	Resist
UV Resistance	DIN 51094	Declared value	No change

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl
Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.
Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters
Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com

Warnings:

- Avoid direct cutting on the surface.
- The use of scouring pads, knives and other cleaning elements that may be rough or abrasive to the surface to be cleaned should be avoided. For example, granule cleaners
- Avoid prolonged contact with industrial objects at very high temperature
- Avoid products that contain hydrofluoric acid and its derivatives. (oven cleaners, for example). Do not use concentrated hydrochloric acid or caustic soda.

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl

Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.

Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters

Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com

TECHNICAL DATA SHEET

20 mm – Honed (GL)

3200x1600x20 mm HONED GL

PHYSICAL-CHEMICAL PROPERTIES	STANDARD TEST	REQUIRED VALUE	AVERAGE VALUE
Water absorption	ISO 10545-3	≤ 0,5%	≤ 0,1%
Breaking strength	ISO 10545-4	≥ 1300 N	> 11000 N
Modulus of rupture	ISO 10545-4	R ≥ 35 N/mm ²	≥ 45 N/mm ²
Impact resistance	ISO-10545-5	Declared value ≥ 0,55 without damage	≥ 0,8
Linear thermal expansion	ISO 10545-8	Declared value	5,7.10 ⁻⁶ °C
Thermal shock resistance	ISO 10545-9	Samples must show no visible defects	Resist
Moisture expansion	ISO 10545-10	Declared value	< 0,1 mm/m
Carzing resistance	ISO 10545-11	Samples must show no surface crazing	Resist
Frost resistance	ISO 10545-12	Samples must show no visible damage	Resist
Chemical resistance: Cleaning products	ISO-10545-13	GB	GA
Chemical resistance: Swimming pool salts	ISO-10545-13	GB	GA
Chemical resistance: Low concentration acids	ISO-10545-13	Declared value	GLA
Chemical resistance: Low concentration bases	ISO-10545-13	Declared value	GLA
Chemical resistance: High concentration acids	ISO-10545-13	Declared value	GHA
Chemical resistance: High concentration bases	ISO-10545-13	Declared value	GHA
Resistance to stains	ISO 10545-14	Declared value	5

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl
Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.
Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters
Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com

Determination of lead and cadmium	ISO 10545-15	Declared value	Cadmium < 0,01 mg/l Lead < 0,1 mg/l
Scratch hardness	UNE 67-101	Declared value	Declared value: min 5
Dry heat resistance	EN 13310	Declared value	Resist
UV Resistance	DIN 51094	Declared value	No change

Warnings:

Avoid products that contain hydrofluoric acid and its derivatives (oven cleaners, for example).

TECHNICAL DATA SHEET

20 mm – Honed (UGL)

3200x1600x20 mm HONED UGL

PHYSICAL-CHEMICAL PROPERTIES	STANDARD TEST	REQUIRED VALUE	AVERAGE VALUE
Water absorption	ISO 10545-3	≤ 0,5%	≤ 0,1%
Breaking strength	ISO 10545-4	≥ 1300 N	> 11000 N
Modulus of rupture	ISO 10545-4	R ≥ 35 N/mm ²	≥ 45 N/mm ²
Impact resistance	ISO-10545-5	Declared value ≥ 0,55 without damage	≥ 0,8
Resistance to deep abrasion	ISO 10545-6	≤ 175 mm ³	≤ 140 mm ³
Linear thermal expansion	ISO 10545-8	Declared value	5,7.10-6.°C
Thermal shock resistance	ISO 10545-9	Samples must show no visible defects	Resist
Moisture expansion	ISO 10545-10	Declared value	< 0,1 mm/m
Frost resistance	ISO 10545-12	Samples must show no visible damage	Resist
Chemical resistance: cleaning products	ISO-10545-13	UB	UA
Chemical resistance: swimming pool salts	ISO-10545-13	UB	UA
Chemical resistance: low concentration acids	ISO-10545-13	Declared value	ULA
Chemical resistance: low concentration bases	ISO-10545-13	Declared value	ULA
Resistance to stains	ISO 10545-14	Declared value	5
Determination of lead and cadmium	ISO 10545-15	Declared value	Cadmium < 0,01 mg/l Lead < 0,1 mg/l
Scratch hardness	UNE 67-101	Declared value	Declared value: min 5
Dry heat resistance	EN 13310	Declared value	Resist
UV Resistance	DIN 51094	Declared value	No change

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl
Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.
Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters
Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com

Warnings:

Avoid products that contain hydrofluoric acid and its derivatives (oven cleaners, for example). Do not use concentrated hydrochloric acid or caustic soda.

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl
Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.
Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters
Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com

TECHNICAL DATA SHEET

20 mm – Moony

3200x1600x20 mm MOONY UGL

PHYSICAL-CHEMICAL PROPERTIES	STANDARD TEST	REQUIRED VALUE	AVERAGE VALUE
Water absorption	ISO 10545-3	≤ 0,5%	≤ 0,1%
Breaking strength	ISO 10545-4	≥ 1300 N	> 11000 N
Modulus of rupture	ISO 10545-4	R ≥ 35 N/mm ²	≥ 45 N/mm ²
Impact resistance	ISO-10545-5	Declared value ≥ 0,55 without damage	≥ 0,8
Resistance to deep abrasion	ISO 10545-6	≤ 175 mm ³	≤ 140 mm ³
Linear thermal expansion	ISO 10545-8	Declared value	5,7.10 ⁻⁶ °C
Thermal shock resistance	ISO 10545-9	Samples must show no visible defects	Resist
Moisture expansion	ISO 10545-10	Declared value	< 0,1 mm/m
Frost resistance	ISO 10545-12	Samples must show no visible damage	Resist
Chemical resistance: cleaning products	ISO-10545-13	UB	UA
Chemical resistance: swimming pool salts	ISO-10545-13	UB	UA
Chemical resistance: low concentration acids	ISO-10545-13	Declared value	ULA
Chemical resistance: low concentration bases	ISO-10545-13	Declared value	ULA
Resistance to stains	ISO 10545-14	Declared value	5
Determination of lead and cadmium	ISO 10545-15	Declared value	Cadmium < 0,01 mg/l Lead < 0,1 mg/l
Scratch hardness	UNE 67-101	Declared value	Declared value: min 7
Dry heat resistance	EN 13310	Declared value	Resist
UV Resistance	DIN 51094	Declared value	No change

Warnings:

Avoid products that contain hydrofluoric acid and its derivatives (oven cleaners, for example). Do not use concentrated hydrochloric acid or caustic soda.

Signed for and behalf of the manufacturer:



Matilde Galende
Laboratory & QA Manager

Alcora, 2020/7/15

BESTSURFACE
BREAKING DESIGN

Best Surface Holding Srl
Via Camperio Manfredo, 14
20123 Milano · Italy
Ph +39 02 58215360
Fax +39 02 58215368
P.IVA/C.F. 10463820968
REA MI-2533743
Cap. Soc. 250.000,00 Euro i.v.

Best Surface S.L.
Carretera de Castellón, 117
y DS Foyes 5 Den Partida
Foyes Ferraes
12110 Alcora · Castellón
NIF/VAT: B-44513752
Ph +34 964 78 45 45
Fax +34 964 78 45 00
Cap. Soc. 10.000.000 Euro i.v.

Headquarters
Via San Clemente 1
20122 Milano · Italy
Ph +39 02 50020754
Fax +39 02 50020764

idylium.com